



GENERAL DESCRIPTION

An asphaltic concrete surface conditioner.

BASIC USE

To enhance the bond of American Hydrotech's Monolithic Membrane 6125 roofing and waterproofing membranes to concrete substrates.

TECHNICAL SPECIFICATIONS

Must conform to ASTM D41-85.

APPLICATION

- Thoroughly clean area to be waterproofed. The area must be thoroughly swept, then blown clean using an air compressor.
- The Surface Conditioner is then spray-applied at a rate of 300-600 square feet per gallon. The result should be a "tanning" of the concrete surface. Over-application may cause adhesion problems between the concrete and MM 6125.
- The Surface Conditioner must be allowed sufficient time to thoroughly dry. NOTE: The cooler the ambient temperature and/or higher the humidity, the more drying time required.
- DO NOT apply Surface Conditioner to wood, plywood, metal or gypsum board substrates - concrete only.
- The Surface Conditioner can be cut-back with unleaded gas if necessary, to facilitate spraying.

CAUTIONS

FLAMMABLE MATERIAL!

Do not use near open fire or flame and extinguish all smoking materials.