

Hydrotech® DuPont™ Styrofoam™ Plazamate™ XR



BUILDING TRUST



formerly known as DuPont™ Styrofoam™ Plazamate™ XR

GENERAL DESCRIPTION

Styrofoam™ Brand Plazamate™ XR is a 60 psi closed cell, rigid plastic, extruded polystyrene foam insulation. Styrofoam™ Brand Plazamate™ XR resists compressive creep and fatigue, delivering long-term compressive strength and high R-values ranging from 6.7 per inch to 7.7 per inch.

BASIC USE

Styrofoam brand insulation is designed for use in roof, wall, and foundation insulation applications in new or retrofit commercial structures. Styrofoam™ Plazamate™ XR is intended for use on top of roofing/waterproofing membranes in ballasted IRMA/PMR (Inverted Roof Membrane Assembly/Protected Membrane Roof) applications. Styrofoam™ Plazamate™ XR boards are intended for use when applications require optimizing roof thickness, reducing expensive commercial roof building alterations required for meeting the latest building and energy codes, and assists in reducing overall project costs.



PRODUCT INFORMATION

- Standard size - 4ft x 8 ft
- Standard thickness - 2.25" (R-15) & 3" (R-20)
- Square Edge

TECHNICAL DATA

PROPERTY	TEST METHOD	PLAZAMATE XR/HI60
THERMAL RESISTANCE ¹		
Aged R-value/inch @75°F (24°C) mean. temp., ft ² *hr*°F/Btu	ASTM C518	6.7
Aged R-value/inch @40°F (4°C) mean. temp., ft ² *hr*°F/Btu	ASTM C518	7.4
Aged R-value/inch @25°F (-4°C) mean. temp., ft ² *hr*°F/Btu	ASTM C518	7.7
COMPREHENSIVE STENGTH ²		
psi, (kPa), min.	ASTM D1621	60 (413)
FLEXURAL STRENGTH		
psi, (kPa), min.	ASTM C203	75 (517)
WATER ABSORPTION		
% by volume, max.	ASTM C272	0.01
WATER VAPOR PERMEANCE ³		
perm, (ng/(Pa*s*m ²))	ASTM E96	0.02
DIMENTIONAL STABILITY		
% linear change, max.	ASTM D2126	0.09
LINEAR COEFFICIENT OF THERMAL EXPANSION		
in./in. *°F, (mm/mm*°C)	ASTM D696	3.5 X 10 ⁻⁵
TYPE	ASTM C578	VII
MAXIMUM USE TEMPERATURE (°F, (°C))	--	165, (74)

LEED® INFORMATION

	Credit 4	Credit 5
Recycled Content (% by weight)	20 (pi)	
Manufacture Location	Contact Hydrotech for project specific information	
Extraction/Harvesting Location	Contact Hydrotech for project specific information	

1. Values are consistent with the criteria of ASTM C578. R means resistance to heat flow. The higher the R-value, the greater the insulating power.
2. Vertical compressive strength is measured at 10 percent deformation or at yield, whichever occurs first. Since Styrofoam™ Brand Extruded Polystyrene Foam Insulation is a visco-elastic material, adequate design safety factors should be used to prevent long-term creep and fatigue deformation. For static loads, 3:1 is suggested. For dynamic loads, 5:1 is suggested.
3. Based on 1" thickness.
4. These numerical flame spread and smoke developed ratings are not intended to reflect hazards presented by this or any other material under actual fire conditions.

*Trademark of the DuPont Chemical Company

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.**

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.